

<b>THOMSON</b>  <b>DELPHION</b>		<b>RESEARCH</b> <a href="#">My Account</a>   <a href="#">Products</a>	<b>PRODUCTS</b> <a href="#">Search: Quick Number</a>   <a href="#">Boolean</a>   <a href="#">Advanced</a>	<b>INSIDE DELPHION</b>
------------------------------------------------------------------------------------------------------------------------	--	--------------------------------------------------------------------------	--------------------------------------------------------------------------------------------------------------	------------------------

## The Delphion Integrated View

Get Now: <input checked="" type="checkbox"/> PDF   <a href="#">More choices...</a>	Tools: Add to Work File: <a href="#">Create new Wo</a>
View: <a href="#">INPADOC</a>   Jump to: <input type="text" value="Top"/> <input checked="" type="checkbox"/> Go to: <a href="#">Derwent...</a>	<input checked="" type="checkbox"/> Email

🔍 Title: **JP6223798A2: SEPARATOR FOR SEALED LEAD-ACID BATTERY**

🔍 Country: **JP Japan**

🔍 Kind: **A**

🔍 Inventor: **YAMADA TAKASHI;  
TSUJINO NAOHIRO;**

🔍 Assignee: **JAPAN STORAGE BATTERY CO LTD**  
[News, Profiles, Stocks and More about this company](#)

🔍 Published / Filed: **1994-08-12 / 1991-02-28**

🔍 Application Number: **JP1991000059651**

🔍 IPC Code: **H01M 2/16;**

🔍 Priority Number: **1991-02-28 JP1991000059651**

🔍 Abstract:

**PURPOSE:** To facilitate a separator isolating process in an automatic electrode group stacking machine and to allow the massproduction of storage batteries by papering a sheet of thin paper on the side of the separator plate with an adhesive.

**CONSTITUTION:** After an adhesive composed of mainly an acryl-based resin or a pp hot melt resin, etc., is applied to and penetrated into the sides 3 of a separator 2 comprising mainly glass fibers, a sheet of thin paper 1 is stuck thereto. This thin paper sheet 1 is made of pulp, etc., and has low surface frictional resistance, and thus positioning the thin paper sheet 1 on at least the single surface of the separator plate 2 facilitates a separator isolating process in an automatic electrode group stacking machine. The thin paper sheet 1 has no acid resistance, so that it is readily dissolved in dilute sulfuric acid, electrolyte, in a storage battery to relate no charge and discharge reaction, facilitating the massproduction of the storage batteries.

**COPYRIGHT:** (C)1994,JPO&Japio

🔍 Family: **None**

🔍 Other Abstract Info: **CHEMABS 121(26)304673S CAN121(26)304673S DERABS C94-297320 DERC94-297320 JAPABS 180586E000113 JAP180586E000113**



[Nominate](#)

[this for the Gallery...](#)